


PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : D21H		A2	(11) International Publication Number: WO 99/55962
			(43) International Publication Date: 4 November 1999 (04.11.99)
(21) International Application Number: PCT/SE99/00678			(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).
(22) International Filing Date: 26 April 1999 (26.04.99)			
(30) Priority Data: 98850067.4 27 April 1998 (27.04.98) EP 60/083,253 27 April 1998 (27.04.98) US			
(71) Applicant (for all designated States except US): AKZO NOBEL N.V. [NL/NL]; P.O. Box 9300, NL-6800 SB Arnhem (NL).			
(71) Applicant (for SE only): EKA CHEMICALS AB [SE/SE]; S-445 80 Bohus (SE).			
(72) Inventors; and (75) Inventors/Applicants (for US only): STRUCK, Oliver [DE/DE]; Oberstrasse 26, D-52349 Düren (DE). HÅLLSTRÖM, Hans [SE/SE]; Knut Stangenbergs väg 162, S-131 47 Nacka (SE). SIKKAR, Rein [SE/SE]; Vesslestigen 2, S-448 34 Floda (SE).			
(74) Agent: NYANDER, Johan; Eka Chemicals AB, Patent Dept., P.O. Box 11556, S-100 61 Stockholm (SE).			Published Without international search report and to be republished upon receipt of that report.
(54) Title: A PROCESS FOR THE PRODUCTION OF PAPER			
(57) Abstract <p>The present invention relates to process for the production of paper from a suspension containing cellulosic fibres, and optional fillers, comprising adding to the suspension drainage and retention aids comprising a cationic organic polymer and anionic microparticulate material, forming and dewatering the suspension on a wire, wherein the cationic organic polymer has a non-aromatic hydrophobic group. The invention further relates to a cationic vinyl addition polymer comprising in polymerized form at least one non-cationic monomer having a non-aromatic hydrophobic group and at least one cationic monomer.</p>			
 <p>Cat contains herself</p> <p>p. 9 anionic polymer particles containing sulfonate</p> <p>p. 12 size including ketene dimer</p>			

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

A process for the production of paper

This invention relates to papermaking and more specifically to a process for the production of paper in which a cationic organic polymer having a hydrophobic group and an anionic microparticulate material are added to a papermaking stock. The process provides improved drainage and retention.

Background

In the papermaking art, an aqueous suspension containing cellulosic fibres, and optional fillers and additives, referred to as stock, is fed into a headbox which ejects the stock onto a forming wire. Water is drained from the stock through the forming wire so that a wet web of paper is formed on the wire, and the web is further dewatered and dried in the drying section of the paper machine. Water obtained by dewatering the stock, referred to as white water, which usually contains fine particles, e.g. fine fibres, fillers and additives, is usually recirculated in the papermaking process. Drainage and retention aids are conventionally introduced into the stock in order to facilitate drainage and increase adsorption of fine particles onto the cellulosic fibres so that they are retained with the fibres on the wire. Cationic organic polymers like cationic starch and cationic acrylamide-based polymers are widely used as drainage and retention aids. These polymers can be used alone but more frequently they are used in combination with other polymers and/or with anionic microparticulate materials such as, for example, anionic inorganic particles like colloidal silica and bentonite.

U.S. Patent Nos. 4,980,025; 5,368,833; 5,603,805; 5,607,552; and 5,858,174; as well as International Patent Application No. WO 97/18351 disclose the use of cationic and amphoteric acrylamide-based polymers and anionic inorganic particles as stock additives in papermaking. These additives are among the most efficient drainage and retention aids now in use. Similar systems are disclosed in European Patent Application No. 805,234.

The Invention

According to the present invention it has been found that improved drainage and retention can be obtained by using drainage and retention aids comprising a cationic organic polymer having a hydrophobic group and an anionic microparticulate material. More specifically, the present invention relates to a process for the production of paper from a suspension containing cellulosic fibres, and optional fillers, which comprises adding to the suspension a cationic organic polymer and an anionic microparticulate material, forming and dewatering the suspension on a wire, wherein the cationic organic polymer has a non-aromatic hydrophobic group. In a preferred aspect of the invention, the process further comprises forming and dewatering the suspension on a wire to obtain a wet web containing cellulosic fibres, or paper, and white water, recirculating the white


water and optionally introducing fresh water to form a suspension containing cellulosic fibres, and optional fillers, to be dewatered to form paper, wherein the amount of fresh water introduced is less than 30 tons per ton of dry paper produced. The invention thus relates to a process as further defined in the claims.

5 The process of this invention results in improved drainage and/or retention and hereby the present process makes it possible to increase the speed of the paper machine and to use lower a dosage of additives to give a corresponding drainage and retention effect, thereby leading to an improved papermaking process and economic benefits. The process of this invention is suitably used for the treatment of cellulosic suspensions in
10 closed mills wherein the white water is repeatedly recycled with the introduction of only low amounts of fresh water. The process is further suitably applied to papermaking processes using cellulosic suspensions having high salt contents, and thus having high conductivity levels, for example processes with extensive white water recycling and limited fresh water supply and/or processes using fresh water having high salt contents.

15 The cationic organic polymer having a hydrophobic group according to this invention, herein also referred to as "main polymer", can be linear, branched or cross-linked, e.g. in the form of a microparticulate material, preferably essentially linear. Preferably the main polymer is water-soluble or water-dispersable. The hydrophobic group of the main polymer is non-aromatic and it can be a pendent group attached to the polymer
20 backbone (main chain) or, preferably, a hydrophobic group attached to a heteroatom, e.g. nitrogen or oxygen, the nitrogen optionally being charged, which heteroatom, in turn, can be attached to the polymer backbone, for example via a chain of atoms. The hydrophobic group has at least 2 and usually at least 3 carbon atoms, suitably from 3 to 12 and preferably from 4 to 8 carbon atoms. The hydrophobic group is suitably a hydrocarbon
25 chain. Examples of suitable hydrophobic groups include linear, branched and cyclic alkyl groups like ethyl; propyl, e.g. n-propyl and iso-propyl; butyl, e.g. n-butyl, iso-butyl and t-butyl; pentyl, e.g. n-pentyl, neo-pentyl and iso-pentyl; hexyl, e.g. n-hexyl and cyclohexyl; heptyl, e.g. n-heptyl and cycloheptyl, octyl, e.g. n-octyl; nonyl, e.g. n-nonyl; decyl, e.g. n-decyl; undecyl, e.g. n-undecyl and dodecyl, e.g. n-dodecyl. The linear and branched chain
30 alkyl groups are generally preferred.


 The main polymer can be selected from homopolymers and copolymers prepared from one or more monomers comprising at least one monomer having a hydrophobic group, suitably an ethylenically unsaturated monomer, and the main polymer is preferably a vinyl addition polymer. The term "vinyl addition polymer", as used herein, refers to a
35 polymer prepared by addition polymerization of vinyl monomers or ethylenically unsaturated monomers which include, for example, acrylamide-based and acrylate-based monomers.

According to a first embodiment of this invention, suitable main polymers include cationic vinyl addition polymers obtained by polymerizing a cationic monomer having a non-aromatic hydrophobic group or a monomer mixture comprising such a monomer. Preferably the cationic monomer having a non-aromatic hydrophobic group is represented by the general formula (I):




wherein R_1 is H or CH_3 ; R_2 and R_3 are each H or, preferably, an alkyl group having from 1 to 3 carbon atoms, suitably 1 to 2 carbon atoms; A is O or NH; B is an alkylene group of from 2 to 8 carbon atoms, suitably 2 to 4 carbon atoms, or a hydroxy propylene group; R_4 is a substituent containing a hydrophobic group, suitably a non-aromatic hydrocarbon group containing at least 2 carbon atoms, suitably from 3 to 12 and preferably from 4 to 8 carbon atoms; and X^- is an anionic counterion, usually a halide like chloride. The group R_4 usually comprises and, preferably, is selected from any of the linear, branched or cyclic alkyl groups mentioned above and the total number of carbon atoms of the groups R_2 , R_3 and R_4 is usually at least 4, suitably at least 5 and preferably at least 6. Examples of suitable cationic monomers having a non-aromatic hydrophobic group include (meth)acryloxyethyl-N,N-dimethyl-N-n-butylammonium chloride, (meth)acryloxyaminoethyl-N,N-dimethyl-N-n-butylammonium chloride, (meth)acryloxypropyl-N,N-dimethyl-N-t-butylammonium chloride, (meth)acryloxyaminopropyl-N,N-dimethyl-N-t-butylammonium chloride, (meth)acryloxyaminopropyl-N,N-dimethyl-N-n-hexylammonium chloride, (meth)acryloxyethyl-N,N-dimethyl-N-n-hexylammonium chloride, (meth)acryloxyethyl-N,N-dimethyl-N-methylcyclohexylammonium chloride, and (meth)acryloxyaminopropyl-N,N-dimethyl-N-methylcyclohexylammonium chloride.

The main polymer can be a homopolymer prepared from a cationic monomer having a non-aromatic hydrophobic group or a copolymer prepared from a monomer mixture comprising a cationic monomer having a non-aromatic hydrophobic group and one or more copolymerizable monomers. Suitable copolymerizable non-ionic monomers include monomers represented by the general formula (II):



wherein R_1 is H or CH_3 ; A is O or NH; B is an alkylene group of from 2 to 8 carbon atoms, suitably 2 to 4 carbon atoms, or a hydroxy propylene group or, alternatively, A and B are both nothing whereby there is a single bond between C and N ($O=C-NR_5R_6$); R_5 and R_6 are each H or a substituent containing a hydrophobic group, suitably a hydrocarbon group, preferably alkyl, having from 1 to 6, suitably from 1 to 4 and usually from 1 to 3 carbon atoms. Examples of suitable copolymerizable monomers of this type include (meth)acrylamide; acrylamide-based monomers like N-alkyl (meth)acrylamides and N,N-dialkyl (meth)acrylamides, e.g. N-n-propylacrylamide, N-isopropyl (meth)acrylamide, N-n-butyl (meth)acrylamide, N-isobutyl (meth)acrylamide and N-t-butyl (meth)acrylamide; and dialkyl-aminoalkyl (meth)acrylamides, e.g. dimethylaminoethyl (meth)acrylamide, diethyl-aminoethyl (meth)acrylamide, dimethylaminopropyl (meth)acrylamide and diethylamino-propyl (meth)acrylamide; acrylate-based monomers like dialkylaminoalkyl (meth)acrylates, e.g. dimethylaminoethyl (meth)acrylate, diethylaminoethyl (meth)acrylate, t-butylaminoethyl (meth)acrylate and dimethylaminohydroxypropyl acrylate; and vinylamides, e.g. N-vinyl-formamide and N-vinylacetamide. Preferred copolymerizable non-ionic monomers include acrylamide and methacrylamide, i.e. (meth)acrylamide, and the main polymer is preferably an acrylamide-based polymer.


Suitable copolymerizable cationic monomers include the monomers represented by the general formula (III):



wherein R_1 is H or CH_3 ; R_2 and R_3 are each H or, preferably, an alkyl group having from 1 to 3 carbon atoms, suitably 1 to 2 carbon atoms; A is O or NH; B is an alkylene group of from 2 to 8 carbon atoms, suitably 2 to 4 carbon atoms, or a hydroxy propylene group; R_7 is H, a hydrocarbon group, suitably alkyl, having from 1 to 3 carbon atoms, suitably 1 to 2 carbon atoms, or a substituent containing an aromatic group, suitably a phenyl or substituted phenyl group, which can be attached to the nitrogen by means of an alkylene group usually having from 1 to 3 carbon atoms, suitably 1 to 2 carbon atoms, for example a benzyl group ($-\text{CH}_2-\text{C}_6\text{H}_5$) or a phenylethyl group ($-\text{CH}_2-\text{CH}_2-\text{C}_6\text{H}_5$); and X^- is an anionic counterion, usually methylsulphate or a halide like chloride. Examples of suitable cationic copolymerizable monomers include acid addition salts and quaternary ammonium salts of the dialkylaminoalkyl (meth)acrylamides and dialkylaminoalkyl (meth)acrylates mentioned


above, usually prepared using acids like HCl, H₂SO₄, etc., or quaternizing agents like methyl chloride, dimethyl sulphate, benzyl chloride, etc.; and dialkyldialkylammonium halides like dialkyldimethylammonium chloride. Copolymerizable anionic monomers like acrylic acid, methacrylic acid, various sulfonated vinyl addition monomers, etc. can also be employed and, preferably, in minor amounts.

According to a second embodiment of this invention, suitable main polymers include cationic vinyl addition polymers obtained by polymerizing a monomer mixture comprising at least one non-cationic ethylenically unsaturated monomer having a non-aromatic hydrophobic group and at least one cationic ethylenically unsaturated monomer, the non-aromatic hydrophobic group being as defined above, and this invention further relates to a cationic vinyl addition polymer having a non-aromatic hydrophobic group, its preparation and use, as further defined in the claims. Suitable non-cationic monomers having a non-aromatic hydrophobic group include non-ionic monomers, preferably a non-ionic monomer represented by the general formula (IV):



wherein R₁ is H or CH₃; A is O or NH; B is an alkylene group of from 2 to 8 carbon atoms, suitably 2 to 4 carbon atoms, or a hydroxy propylene group or, alternatively, A and B are both nothing whereby there is a single bond between C and N (O=C-NR₈R₉); R₈ and R₉ are each H or a substituent containing a hydrophobic group, suitably a hydrocarbon group, preferably alkyl, having from 1 to 6 carbon atoms, at least one of R₈ and R₉ being a substituent containing a hydrophobic group, suitably an alkyl group, having from 2 to 6 and preferably 3 to 4 carbon atoms. The total number of carbon atoms of the groups R₈ and R₉ is usually at least 2, suitably at least 3 and notably from 3 to 6. Examples of suitable copolymerizable monomers of this type include acrylamide-based monomers like N-alkyl (meth)acrylamides, e.g. N-ethyl (meth)acrylamide, N-n-propyl (meth)acrylamide, N-isopropyl (meth)acrylamide, N-n-butyl (meth)acrylamide, N-t-butyl (meth)acrylamide, N-isobutyl (meth)acrylamide, N-n-butoxymethyl (meth)acrylamide, and N-isobutoxymethyl (meth)acrylamide; N-alkylaminoalkyl (meth)acrylamides; N,N-dialkylaminoalkyl (meth)acrylamides, as well as acrylate-based monomers like N-alkylaminoalkyl (meth)acrylates and N,N-dialkylaminoalkyl (meth)acrylates, e.g. t-butylamino-2-ethyl (meth)acrylate.

Further suitable non-cationic monomers having a non-aromatic hydrophobic group include non-ionic monomers represented by the general formula (V):



5

wherein R_1 is H or CH_3 ; A is O or NH; B is an alkylene group of from 2 to 4 carbon atoms, suitably 2 to 3 carbon atoms, preferably ethylene ($-\text{CH}_2-\text{CH}_2-$) or propylene ($-\text{CH}_2-\text{CH}(\text{CH}_3)-$ or $-\text{CH}(\text{CH}_3)-\text{CH}_2-$); n is an integer of at least 1, suitably from 2 to 40 and preferably 3 to 20; R_{10} is a substituent containing a hydrophobic group, suitably alkyl, having at least 2 carbon atoms, suitably from 3 to 12 and preferably from 4 to 8 carbon atoms. Examples of suitable copolymerizable monomers of this type include alkyl (mono-, di- and polyethyleneglycol) (meth)acrylates and alkyl (mono-, di- and polypropyleneglycol) (meth)acrylates, e.g. ethyltriglycol (meth)acrylate and butyldiglycol (meth)acrylate.

15 The cationic monomer can be selected from any of the cationic monomers mentioned above, including the cationic monomers represented by the general formulae (I) and (III) as well as diallyldialkylammonium halides like diallyldimethylammonium chloride. The monomer mixture according to the second embodiment may also comprise other copolymerizable monomers such as, for example, the non-ionic monomers represented by
20 the general formula (II) above which may not have a hydrophobic group, suitably acrylamide and methacrylamide, and the anionic monomers mentioned above.

Main polymers according to this invention can be prepared from a monomer mixture generally comprising from 1 to 99 mole%, suitably from 2 to 50 mole% and preferably from 5 to 25 mole% of monomer having a non-aromatic hydrophobic group, and
25 from 99 to 1 mole%, suitably from 98 to 50 mole% and preferably from 95 to 75 mole% of other copolymerizable monomers which preferably comprises acrylamide or methacrylamide ((meth)acrylamide), the monomer mixture suitably comprising from 98 to 50 mole% and preferably from 95 to 75 mole% of (meth)acrylamide, the sum of percentages being 100. According to the first embodiment of this invention, the monomer having a non-
30 aromatic hydrophobic group is cationic. According to the second embodiment of this invention, the monomer having a non-aromatic hydrophobic group is non-cationic and the monomer mixture thus also comprises a copolymerizable cationic monomer which suitably is present in an amount of from 2 to 50 mole% and preferably from 5 to 25 mole%.

The main polymer according to this invention can be prepared by polymerization
35 of monomers in known manner and the polymerization is suitably carried out in an aqueous or inverse emulsion phase. The monomer(s) used, including the monomer having a hydrophobic group described above, are preferably at least in part soluble in the aqueous phase. Polymerization processes are generally known in the art and reference is made to

Encyclopedia of Polymer Science and Engineering, Vol. 1-18, John Wiley & Sons, 1985, which is hereby incorporated herein by reference. The polymerization is suitably initiated in an aqueous phase containing monomers, a conventional free-radical polymerization initiator and optionally chain-transfer agent for modifying the molecular weight of the polymer, and is suitably carried out in the absence of oxygen in an inert gas atmosphere, for example under nitrogen. The polymerization suitably takes place under stirring at temperatures between 20 and 100°C, preferably between 40 and 90°C.

Usually the charge density of the main polymer is from 0.2 to 5.0 meqv/g of dry polymer, suitably from 0.6 to 3.0. The weight average molecular weight of synthetic main polymers is usually at least about 500,000, suitably above about 1,000,000 and preferably above about 2,000,000. The upper limit is not critical; it can be about 30,000,000, usually 25,000,000 and suitably 20,000,000.

The main polymer of this invention may be in any state of aggregation such as, for example, in solid form, e.g. powders, in liquid form, e.g. solutions, emulsions, dispersions, including salt dispersions, etc. When being added to the stock, the main polymer is suitably in liquid form, e.g. in the form of an aqueous solution or dispersion.

The anionic microparticulate material according to this invention can be selected from inorganic and organic particles. Anionic inorganic particles that can be used according to the invention include anionic silica-based particles and clays of the smectite type. It is preferred that the anionic inorganic particles are in the colloidal range of particle size. Anionic silica-based particles, i.e. particles based on SiO_2 or silicic acid, are preferably used and such particles are usually supplied in the form of aqueous colloidal dispersions, so-called sols. Examples of suitable silica-based particles include colloidal silica and different types of polysilicic acid. The silica-based sols can also be modified and contain other elements, e.g. aluminium and/or boron, which can be present in the aqueous phase and/or in the silica-based particles. Suitable silica-based particles of this type include colloidal aluminium-modified silica and aluminium silicates. Mixtures of such suitable silica-based particles can also be used. Drainage and retention aids comprising suitable anionic silica-based particles are disclosed in U.S. Patent Nos. 4,388,150; 4,927,498; 4,954,220; 4,961,825; 4,980,025; 5,127,994; 5,176,891; 5,368,833; 5,447,604; 5,470,435; 5,543,014; 5,571,494; 5,573,674; 5,584,966; 5,603,805; 5,688,482; and 5,707,493; which are hereby incorporated herein by reference.

Anionic silica-based particles suitably have an average particle size below about 50 nm, preferably below about 20 nm and more preferably in the range of from about 1 to about 10 nm. As conventional in silica chemistry, the particle size refers to the average size of the primary particles, which may be aggregated or non-aggregated. The specific surface

area of the silica-based particles is suitably above 50 m²/g and preferably above 100 m²/g. Generally, the specific surface area can be up to about 1700 m²/g and preferably up to 1000 m²/g. The specific surface area can be measured by means of titration with NaOH in known manner, e.g. as described by Sears in Analytical Chemistry 28(1956):12, 1981-1983
5 and in U.S. Patent No. 5,176,891. The given area thus represents the average specific surface area of the particles.

In a preferred embodiment of the invention, the anionic inorganic particles are silica-based particles having a specific surface area within the range of from 50 to 1000 m²/g, preferably from 100 to 950 m²/g. Sols of silica-based particles these types also
10 encompass modified sols like aluminium-containing silica-based sols and boron-containing silica-based sols. Preferably, the silica-based particles are present in a sol having an S-value in the range of from 8 to 45%, preferably from 10 to 30%, containing silica-based particles with a specific surface area in the range of from 300 to 1000 m²/g, suitably from 500 to 950 m²/g, and preferably from 750 to 950 m²/g, which sols can be modified with
15 aluminium and/or boron as mentioned above. For example, the particles can be surface-modified with aluminium to a degree of from 2 to 25% substitution of silicon atoms. The S-value can be measured and calculated as described by Iler & Dalton in J. Phys. Chem. 60(1956), 955-957. The S-value indicates the degree of aggregate or microgel formation and a lower S-value is indicative of a higher degree of aggregation.

20 In yet another preferred embodiment of the invention, the silica-based particles are selected from polysilicic acid and modified polysilicic acid having a high specific surface area, suitably above about 1000 m²/g. The specific surface area can be within the range of from 1000 to 1700 m²/g and preferably from 1050 to 1600 m²/g. The sols of modified polysilicic acid can contain other elements, e.g. aluminium and/or boron, which can be
25 present in the aqueous phase and/or in the silica-based particles. In the art, polysilicic acid is also referred to as polymeric silicic acid, polysilicic acid microgel, polysilicate and polysilicate microgel, which are all encompassed by the term polysilicic acid used herein. Aluminium-containing compounds of this type are commonly also referred to as polyaluminosilicate and polyaluminosilicate microgel, which are both encompassed by the
30 terms colloidal aluminium-modified silica and aluminium silicate used herein.

Clays of the smectite type that can be used in the process of the invention are known in the art and include naturally occurring, synthetic and chemically treated materials. Examples of suitable smectite clays include montmorillonite/bentonite, hectorite, beidelite, nontronite and saponite, preferably bentonite and especially such bentonite which after
35 swelling preferably has a surface area of from 400 to 800 m²/g. Suitable clays are disclosed

in U.S. Patent Nos. 4,753,710; 5,071,512; and 5,607,552, which are hereby incorporated herein by reference.

Anionic organic particles that can be used according to the invention include highly cross-linked anionic vinyl addition polymers, suitably copolymers comprising an anionic monomer like acrylic acid, methacrylic acid and sulfonated or phosphonated vinyl addition monomers, usually copolymerized with nonionic monomers like (meth)acrylamide, alkyl (meth)acrylates, etc. Useful anionic organic particles also include anionic condensation polymers, e.g. melamine-sulfonic acid sols.

In addition to the cationic organic polymer having a hydrophobic group and the anionic microparticulate material, the drainage and retention aids (agents) according to the present invention may also comprise further components such as, for example, low molecular weight cationic organic polymers and/or aluminium compounds. The term "drainage and retention aids", as used herein, refers to two or more components (aids, agents or additives) which, when being added to a stock, give better drainage and/or retention than is obtained when not adding the components.

Low molecular weight (hereinafter LMW) cationic organic polymers that can be used include those commonly referred to and used as anionic trash catchers (ATC). ATC's are known in the art as neutralizing and/or fixing agents for detrimental anionic substances present in the stock and the use thereof in combination with drainage and retention aids often provide further improved drainage and/or retention. The LMW cationic organic polymer can be derived from natural or synthetic sources, and preferably it is an LMW synthetic polymer. Suitable organic polymers of this type include LMW highly charged cationic organic polymers such as polyamines, polyamidoamines, polyethyleneimines, homo- and copolymers based on diallyldimethyl ammonium chloride, (meth)acrylamides and (meth)acrylates. In relation to the molecular weight of the main polymer, the molecular weight of the LMW cationic organic polymer is usually lower; it is suitably at least 2,000 and preferably at least 10,000. The upper limit of the molecular weight is usually about 700,000, suitably about 500,000 and preferably about 200,000.

Aluminium compounds that can be used according to this invention include alum, aluminates, aluminium chloride, aluminium nitrate and polyaluminium compounds, such as polyaluminium chlorides, polyaluminium sulphates, polyaluminium compounds containing both chloride and sulphate ions, polyaluminium silicate-sulphates, and mixtures thereof. The polyaluminium compounds may also contain other anions than chloride ions, for example anions from sulfuric acid, phosphoric acid, organic acids such as citric acid and oxalic acid.

The components of drainage and retention aids according to the invention can be added to the stock in conventional manner and in any order. It is preferred to add the main polymer to the stock before adding the anionic microparticulate material, even if the opposite order of addition may be used. It is further preferred to add the main polymer before a shear stage, which can be selected from pumping, mixing, cleaning, etc., and to add the anionic particles after that shear stage. When using an LMW cationic organic polymer and/or an aluminium compound, such components are preferably introduced into the stock prior to introducing the main polymer and anionic microparticulate material. Alternatively, the LMW cationic organic polymer and the main polymer can be introduced into the stock essentially simultaneously, either separately or in admixture, e.g. as disclosed in U.S. Patent No. 5,858,174, which is hereby incorporated herein by reference.

The components of the present drainage and retention aids are added into the stock to be dewatered in amounts which can vary within wide limits depending on, inter alia, type and number of components, type of furnish, filler content, type of filler, point of addition, salt content, etc. Generally the components are added in an amount that give better drainage and/or retention than is obtained when not adding the components. The main polymer is usually added in an amount of at least 0.001%, often at least 0.005% by weight, based on dry stock substance, and the upper limit is usually 3% and suitably 1.5% by weight. The anionic microparticulate material is usually added in an amount of at least 0.001% by weight, often at least 0.005% by weight, based on dry substance of the stock, and the upper limit is usually 1.0% and suitably 0.6% by weight. When using anionic silica-based particles, the total amount added is suitably within the range of from 0.005 to 0.5% by weight, calculated as SiO_2 and based on dry stock substance, preferably within the range of from 0.01 to 0.2% by weight. When using an LMW cationic organic polymer in the process, it can be added in an amount of at least 0.05%, based on dry substance of the stock to be dewatered. Suitably, the amount is in the range of from 0.07 to 0.5%, preferably in the range from 0.1 to 0.35%. When using an aluminium compound in the process, the total amount introduced into the stock to be dewatered is dependent on the type of aluminium compound used and on other effects desired from it. It is for instance well known in the art to utilise aluminium compounds as precipitants for rosin-based sizing agents. The total amount added is usually at least 0.05%, calculated as Al_2O_3 and based on dry stock substance. Suitably the amount is in the range of from 0.5 to 3.0%, preferably in the range from 0.1 to 2.0%.

The process of the invention is preferably used in the manufacture of paper from a suspension containing cellulosic fibres, and optional fillers, having a high conductivity. Usually, the conductivity of the stock that is dewatered on the wire is at least 0.75 mS/cm,

suitably at least 2.0 mS/cm, preferably at least 3.5 mS/cm. Very good results have been observed at conductivity levels above 5.0 mS/cm and even above 7.5 mS/cm. Conductivity can be measured by standard equipment such as, for example, a WTW LF 539 instrument supplied by Christian Berner. The values referred to above are suitably determined by measuring the conductivity of the cellulosic suspension that is fed into or present in the headbox of the paper machine or, alternatively, by measuring the conductivity of white water obtained by dewatering the suspension. High conductivity levels mean high contents of salts (electrolytes), where the various salts can be based on mono-, di- and multivalent cations like alkali metals, e.g. Na^+ and K^+ , alkaline earths, e.g. Ca^{2+} and Mg^{2+} , aluminium ions, e.g. Al^{3+} , $\text{Al}(\text{OH})^{2+}$ and polyaluminium ions, and mono-, di- and multivalent anions like halides, e.g., Cl^- , sulfates, e.g. SO_4^{2-} and HSO_4^- , carbonates, e.g. CO_3^{2-} and HCO_3^- , silicates and lower organic acids. The invention is particularly useful in the manufacture of paper from stocks having high contents of salts of di- and multivalent cations, and usually this content is at least 200 ppm, suitably at least 300 ppm and preferably at least 400 ppm. The salts can be derived from the cellulosic fibres and fillers used to form the stock, in particular in integrated mills where a concentrated aqueous fibre suspension from the pulp mill normally is mixed with water to form a dilute suspension suitable for paper manufacture in the paper mill. The salt may also be derived from various additives introduced into the stock, from the fresh water supplied to the process, or be added deliberately, etc. Further, the content of salts is usually higher in processes where white water is extensively recirculated, which may lead to considerable accumulation of salts in the water circulating in the process.

Accordingly, the invention is further suitably used in papermaking processes where white water is extensively recirculated (recycled), i.e. with a high degree of white water closure, for example where from 0 to 30 tons of fresh water are used per ton of dry paper produced, usually less than 20, suitably less than 15, preferably less than 10 and notably less than 5 tons of fresh water per ton of paper. Recirculation of white water obtained in the process suitably comprises mixing the white water with cellulosic fibres and/or optional fillers to form a suspension to be dewatered; preferably it comprises mixing the white water with a suspension containing cellulosic fibres, and optional fillers, before the suspension enters the forming wire for dewatering. The white water can be mixed with the suspension before, between or after introducing the drainage and retention aids. Fresh water can be introduced in the process at any stage; for example, it can be mixed with cellulosic fibres in order to form a suspension, and it can be mixed with a suspension containing cellulosic fibres to dilute it so as to form the suspension to be dewatered, before

or after mixing the stock with white water and before, between or after introducing the drainage and retention aids.

Further additives which are conventional in papermaking can of course be used in combination with the additives according to the invention, such as, for example, dry strength agents, wet strength agents, sizing agents, e.g. those based on rosin, ketene dimers and acid anhydrides, optical brightening agents, dyes, etc. The cellulosic suspension, or stock, can also contain mineral fillers of conventional types such as, for example, kaolin, china clay, titanium dioxide, gypsum, talc and natural and synthetic calcium carbonates such as chalk, ground marble and precipitated calcium carbonate.

The process of this invention is used for the production of paper. The term "paper", as used herein, of course include not only paper and the production thereof, but also other sheet or web-like products, such as for example board and paperboard, and the production thereof. The process can be used in the production of paper from different types of suspensions of cellulose-containing fibres and the suspensions should suitably contain at least 25% by weight and preferably at least 50% by weight of such fibres, based on dry substance. The suspensions can be based on fibres from chemical pulp such as sulphate, sulphite and organosolv pulps, mechanical pulp such as thermomechanical pulp, chemothermomechanical pulp, refiner pulp and groundwood pulp, from both hardwood and softwood, and can also be based on recycled fibres, optionally from de-inked pulps, and mixtures thereof.

The invention is further illustrated in the following Examples which, however, are not intended to limit the same. Parts and % relate to parts by weight and % by weight, respectively, unless otherwise stated.

25

Example 1

Cationic polymers were prepared by polymerizing a monomer mixture according to the following general procedure:

Monomers and an initiator, 2,2'-azobis(2-amidinopropane) dihydrochloride (Wako V-50) were added to an aqueous phase and polymerization was carried out for about 24 hours at 45°C with stirring under a nitrogen atmosphere. The cationic polymer, which was obtained as a clear gel, was dissolved in water and used as an 0.1% aqueous solution.

Polymers according to the invention, P1 to P5, and polymers intended for comparison purposes, Ref. 1 and Ref. 2, were prepared from the indicated monomers in the indicated amounts:

P1: acrylamide (90 mole%), and
acryloxyethyl dimethyl n-butylammonium chloride (10 mole%);

- P2: acrylamide (90 mole%) and
acryloxyethyl dimethyl methylcyclohexylammonium chloride (10 mole%);
- P3: acrylamide (90 mole%),
methacryloxyaminopropyl trimethylammonium chloride (5 mole%), and
5 methacryloxyethyl t-butylamine (5 mole%);
- P4: acrylamide (90 mole%),
methacryloxyaminopropyltrimethylammonium chloride (5 mole%), and
N-isopropylacrylamide (5 mole%);
- P5: acrylamide (90 mole%),
10 methacryloxyaminopropyltrimethylammonium chloride (5 mole%), and
N-t-butylacrylamide (5 mole%);
- Ref. 1: acrylamide (90 mole%), and
acryloxyethyl trimethylammonium chloride (10 mole%).
- Ref. 2: acrylamide (95 mole%), and
15 acryloxyethyl trimethylammonium chloride (5 mole%).

Example 2

Drainage and retention performance was evaluated by means of a Dynamic Drainage Analyser (DDA), available from Akribi, Sweden, which measures the time for
20 draining a set volume of stock through a wire when removing a plug and applying vacuum to that side of the wire opposite to the side on which the stock is present. First pass retention was evaluated by measuring, with a nephelometer, the turbidity of the filtrate, the white water, obtained by draining the stock.

The furnish used was based on 56% by weight of peroxide bleached TMP/SGW
25 pulp (80/20), 14% by weight of bleached birch/pine sulphate pulp (60/40) refined to 200° CSF and 30% by weight of china clay. To the stock was added 40 g/l of a colloidal fraction, bleach water from an SC mill, filtrated through a 5 µm screen and concentrated with an UF filter, cut off 200,000. Stock volume was 800 ml, consistency 0.14% and pH 7.0. Conductivity was adjusted to about 2.5 mS/cm by addition of calcium chloride (400
30 ppm Ca).

The stock was stirred in a baffled jar at a speed of 1500 rpm throughout the test and additions were conducted as follows: i) adding cationic polymer to the stock following by stirring for 30 seconds, ii) adding anionic microparticulate material to the stock followed by stirring for 15 seconds, iii) draining the stock while automatically recording
35 the drainage time.

The cationic polymers tested in this Example were P1 and Ref. 1 according to in Example 1. The anionic microparticulate material used in this Example was a sol of silica-based particles of the type disclosed in U.S. Patent No. 5,368,833. The sol had an S-value of about 25% and contained silica particles with a specific surface area of about 900 m²/g which were surface-modified with aluminium to a degree of 5%. The silica-based sol was added to the stock in an amount of 1.5 kg/ton, calculated as SiO₂ and based on dry stock system.

Table 1 shows the dewatering time and retention values at various dosages of P1 and Ref. 1, calculated as dry polymer on dry stock system (kg/ton).

Table 1

Cationic Polymer	Dewatering time (sec) / Turbidity (NTU) at indicated Polymer dosage			
	0.5 kg/t	1.0 kg/t	1.5 kg/t	2.0 kg/t
P1	11.6/48	8.9/34	5.8/32	4.7/14
Ref. 1	12.0/57	9.0/49	6.5/36	5.1/28

Example 3

In this test series, dewatering and retention performance was evaluated according to the procedure described in Example 2.

The furnish was the same as used in Example 2. Stock volume was 800 ml, pH about 7 and conductivity was adjusted to 7.0 mS/cm by addition of calcium chloride (1300 ppm Ca), thus simulating a high electrolyte content and a high degree of white water closure.

The anionic inorganic material according to Example 2 were similarly used in this Example and was added in an amount of 1.5 kg/ton, calculated as SiO₂ and based on dry stock system.

The polymers used in this Example were P1, P2 and Ref. 1 according to Example 1. Table 2 shows the dewatering and retention effect at various dosages of P1, P2 and Ref. 1, calculated as dry polymer on dry stock system.

Table 2

Cationic Polymer	Dewatering time (sec) / Turbidity (NTU) at Polymer dosage of			
	0.5 kg/t	1.0 kg/t	1.5 kg/t	2.0 kg/t
P1	11.0/ -	8.7/49	6.3/40	6.0/38
P2	10.7/ -	7.9/50	6.1/43	5.5/32
Ref. 1	12.1/ -	9.5/57	8.8/47	7.8/43

Example 4

In this test series, dewatering and retention performance was evaluated according to the procedure described in Example 2.

The stock used in this Example was similar to the stock used according to Example 3 and had a conductivity of about 7.0 mS/cm (1300 ppm Ca). The anionic inorganic material according to Example 2 was added in an amount of 1.5 kg/ton, calculated as SiO₂ and based on dry stock system. The polymers used were P3 and Ref. 1 according to Example 1.

Table 3 shows the results of the dewatering tests at various dosages of P3 and Ref. 1, calculated as dry polymer on dry stock system.

Table 3

Cationic Polymer	Dewatering time (sec) at Polymer dosage of			
	0.5 kg/t	1.0 kg/t	1.5 kg/t	2.0 kg/t
P3	13.2	10.0	7.4	5.6
Ref. 1	15.5	12.1	10.6	10.2

Example 5

In this test series, the dewatering performance was evaluated according to the procedure described in Example 2.

The stock used in this test series was similar to the one according to Example 2 and had a conductivity of about 2.5 mS/cm. The polymers used were P4, P5 and Ref. 2 according to Example 1 which were added in an amount of 2 kg/ton, calculated as dry polymer on dry stock system. The anionic inorganic material according to Example 2 was similarly used in this test series.

Table 4 shows the results of the dewatering tests at various dosages of anionic inorganic material, calculated as SiO₂ and based on dry stock system.

Table 4

Cationic Polymer	Dewatering time (sec) at SiO ₂ dosage of			
	0.5 kg/t	1.0 kg/t	1.5 kg/t	2.0 kg/t
P4	11.3	10.1	9.8	9.1
P5	11.8	9.5	8.8	8.5
Ref. 2	11.9	10.7	10.3	9.9

Example 6

In this test series, dewatering and retention performance was evaluated according to the procedure described in Example 2.

The furnish was the same as used in Example 2. Stock volume was 800 ml and pH about 7. Sodium chloride (550 ppm Na) and calcium chloride were added to the stock to adjusted the conductivity to 5.0 mS/cm (400 ppm Ca) and 7.0 mS/cm (1300 ppm Ca).

The polymers P2, P3, Ref. 1 and anionic microparticles according to Example 1 were similarly used in this test series in conjunction with a low molecular weight cationic polyamine. The polyamine was added to the stock followed by stirring for 30 seconds before addition of the cationic acrylamide-based polymer. The polyamine was added in an amount of 3 kg/ton, calculated as dry polymer on dry stock system. The main polymers P2, P3 and Ref. 1 were added in an amount of 1.5 kg/ton, calculated as dry polymer on dry stock system.

Table 5 shows the dewatering and retention effect at various conductivities and dosages of silica-based particles, calculated as SiO₂ and based on dry stock system.

Table 5

Test Series No.	SiO ₂ Dosage (kg/t)	Conductivity (mS/cm)	Dewatering time (sec) / Turbidity (NTU) by using the indicated Cationic Polymer		
			P2	P3	Ref. 1
20 1	1.5	5.0	6.9/-	-/39	7.2/51
2	1.5	7.0	16.2/-	-/56	24.7/60
3	1.0	7.0	7.8/-	-/50	13.3/55

Example 7

In this test series, dewatering and retention performance was evaluated according to the procedure described in Example 2.

The furnish was the same as used in Example 2. Stock volume was 800 ml and pH about 7. Varying amounts of sodium chloride was added to the stock to adjust the conductivity to 2.5 mS/cm (550 ppm Na) (Test Series Nos. 1-3), 5.0 mS/cm (1470 ppm Na) (Test Series Nos. 4-6) and 10.0 mS/cm (3320 ppm Na) (Test Series Nos. 7-9).

The cationic polymers used were P1 to P3 and Ref. 1 according to Example 1. The anionic microparticulate material used was hydrated suspension of powdered Na-bentonite in water.

Table 6 shows the dewatering and retention effect at various dosages of cationic polymer, calculated as dry polymer on dry stock system, and bentonite, calculated as dry on dry stock system.

Table 6

	Test Series No.	Polymer Dosage (kg/t)	Bentonite Dosage (kg/t)	Dewatering time (sec) / Turbidity (NTU) by using the indicated Cationic Polymer			
				P1	P2	P3	R f. 1
5	1	2	4	6.6/25	8.5/-	7.5/-	8.9/39
	2	2	8	6.3/29	7.9/-	7.2/-	8.3/37
	3	4	8	4.2/10	4.6/-	4.9/-	8.4/15
10	4	2	4	7.0/30	8.4/-	8.9/-	8.8/42
	5	2	8	6.6/28	8.0/-	8.4/-	8.6/40
	6	4	8	4.8/10	5.0/-	4.8/-	6.6/28
	7	2	4	7.9/22	8.0/-	8.2/-	9.1/45
15	8	2	8	7.4/30	7.2/-	7.1/-	8.2/48
	9	2	8	5.2/11	4.8/-	5.2/-	7.5/28

Claims

1. A process for the production of paper from a suspension containing cellulosic fibres, and optional fillers, comprising adding to the suspension drainage and retention aids comprising a cationic organic polymer and anionic microparticulate material, forming
 5 and dewatering the suspension on a wire, characterised in that the cationic organic polymer has a non-aromatic hydrophobic group.

2. A process according to claim 1, characterised in that the cationic organic polymer is a vinyl addition polymer comprising in polymerized form one or more monomers comprising at least one cationic monomer having a non-aromatic hydrophobic
 10 group.


3. A process according to claim 1 or 2, characterised in that the cationic organic polymer is a vinyl addition polymer comprising in polymerized form at least one non-cationic monomer having a non-aromatic hydrophobic group and at least one cationic monomer.

4. A process according to claim 1, 2 or 3, characterised in that the hydrophobic group is attached to a nitrogen or oxygen which, in turn, is attached to the polymer backbone via a chain of atoms.

5. A process according to claim 1, 2, 3 or 4, characterised in that the hydrophobic group is an alkyl group containing from 3 to 12 carbon atoms.


6. A process according to any of the preceding claims, characterised in that the cationic organic polymer is an acrylamide-based polymer.

7. A process according to any of the preceding claims, characterised in that the cationic organic polymer comprises in polymerized form a cationic monomer having a non-aromatic hydrophobic group represented by the general formula (I):




wherein R_1 is H or CH_3 ; R_2 and R_3 are each an alkyl group having from 1 to 2 carbon atoms; A is O or NH; B is an alkylene group of from 2 to 8 carbon atoms or a hydroxy propylene group; R_4 is a substituent containing an alkyl group containing from 4 to 8
 35 carbon atoms; and X^- is an anionic counterion.

8. A process according to any of the preceding claims, characterised in that the cationic organic polymer comprises in polymerized form a non-ionic monomer having a non-aromatic hydrophobic group represented by the general formula (IV):



5 wherein R_1 is H or CH_3 ; A is O or NH; B is an alkylene group of from 2 to 8 carbon atoms or a hydroxy propylene group or, alternatively, A and B are both nothing whereby there is a single bond between C and N ($\text{O}=\text{C}-\text{NR}_8\text{R}_9$); R_8 and R_9 are each H or a substituent containing an alkyl group having from 1 to 6 carbon atoms, at least one of R_8 and R_9 being a substituent containing an alkyl group having from 2 to 6 carbon atoms.

9. A process according to any of the preceding claims, characterized in that the cationic organic polymer comprises in polymerized form a non-ionic monomer having a non-aromatic hydrophobic group represented by the general formula (V):



20

wherein R_1 is H or CH_3 ; A is O; B is an alkylene group of from 2 to 4 carbon atoms; n is an integer of at least 1; R_{10} is alkyl having at least 2 carbon atoms.

10. A process according to any of the preceding claims, characterized in that the cationic organic polymer is a vinyl addition polymer prepared from a monomer mixture comprising from 5 to 25 mole% of monomer having a non-aromatic hydrophobic group, and from 95 to 75 mole% of other copolymerizable monomers.

11. A process according to any of the preceding claims, characterized in that the anionic microparticulate material is selected from silica-based particles and bentonite.

12. A process according to any of the preceding claims, characterized in that the drainage and retention aids further comprises a low molecular weight cationic organic polymer.

13. A process according to any of the preceding claims, characterized in that the suspension that is dewatered on the wire has a conductivity of at least 2.0 mS/cm.

14. A process according to any of the preceding claims, characterized in that the process further comprises dewatering the suspension on a wire to obtain a wet web of paper and white water, recirculating the white water and optionally introducing fresh water to form a suspension containing cellulosic fibres, and optional fillers, to be dewatered,

wherein the amount of fresh water introduced is less than 30 tons per ton of dry paper produced.

15 15. A process according to any of the preceding claims, characterised in that less than 10 tons of fresh water is introduced into the process per ton of dry paper produced.


16. A cationic vinyl addition polymer comprising in polymerized form at least one non-cationic monomer having a non-aromatic hydrophobic group and at least one cationic monomer.

10 17. A cationic vinyl addition polymer according to claim 16, characterised in that the hydrophobic group is attached to a nitrogen or oxygen which, in turn, is attached to the polymer backbone via a chain of atoms.

18. A cationic vinyl addition polymer according to claim 16 or 17, characterised in that the hydrophobic group is an alkyl group containing from 3 to 12 carbon atoms.


15 19. A cationic vinyl addition polymer according to claim 16, 17 or 18, characterised in that the cationic vinyl addition polymer is an acrylamide-based polymer.

20 20. A cationic vinyl addition polymer according to claim 16, 17, 18 or 19, characterised in that the cationic vinyl addition polymer comprises in polymerized form a non-ionic monomer having a non-aromatic hydrophobic group represented by the general formula (IV):



25 30 wherein R_1 is H or CH_3 ; A is O or NH; B is an alkylene group of from 2 to 8 carbon atoms or a hydroxy propylene group or, alternatively, A and B are both nothing whereby there is a single bond between C and N ($\text{O}=\text{C}-\text{NR}_8\text{R}_9$); R_8 and R_9 are each H or a substituent containing an alkyl group having from 1 to 6 carbon atoms, at least one of R_8 and R_9 being a substituent containing an alkyl group having from 2 to 6 carbon atoms.


35 21. A cationic vinyl addition polymer according to any of claims 16 to 20, characterised in that the cationic vinyl addition polymer comprises in polymerized form a non-ionic monomer having a non-aromatic hydrophobic group represented by the general formula (V):



5

wherein R_1 is H or CH_3 ; A is O or NH; B is an alkylene group of from 2 to 4 carbon atoms; n is an integer of at least 1; R_{10} is alkyl having at least 2 carbon atoms.


22. A cationic vinyl addition polymer according to any of claims 16 to 21, characterised in that the cationic vinyl addition polymer comprises in polymerized form a cationic monomer represented by the general formula (I):



15

wherein R_1 is H or CH_3 ; R_2 and R_3 are each H or an alkyl group having from 1 to 3 carbon atoms; A is O or NH; B is an alkylene group of from 2 to 4 carbon atoms or a hydroxy propylene group; R_4 is a non-aromatic hydrocarbon group containing from 4 to 8 carbon atoms; and X^- is an anionic counterion.

23. A cationic vinyl addition polymer according to any of claims 16 to 22, characterised in that the cationic vinyl addition polymer comprises in polymerized form a cationic monomer represented by the general formula (III):



30

wherein R_1 is H or CH_3 ; R_2 and R_3 are each H or an alkyl group having from 1 to 3 carbon atoms, suitably 1 to 2 carbon atoms; A is O or NH; B is an alkylene group of from 2 to 8 carbon atoms, suitably 2 to 4 carbon atoms, or a hydroxy propylene group; R_7 is H, an alkyl group having from 1 to 3 carbon atoms, a benzyl group or a phenylethyl group; and X^- is an anionic counterion.

24. A cationic vinyl addition polymer according to any of claims 16 to 23, characterised in that the cationic vinyl addition polymer is prepared from a monomer mixture comprising from 5 to 25 mole% of non-ionic monomer having a non-aromatic hydrophobic group, and from 95 to 75 mole% of other copolymerizable monomers.

40

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 6 : D21H 17/71, C08F 220/56, // D21H 17:20, 17:68, 21:10		A3	(11) International Publication Number: WO 99/55962
			(43) International Publication Date: 4 November 1999 (04.11.99)
(21) International Application Number: PCT/SE99/00678		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).	
(22) International Filing Date: 26 April 1999 (26.04.99)		Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>	
(30) Priority Data: 98850067.4 27 April 1998 (27.04.98) EP 60/083,253 27 April 1998 (27.04.98) US			
(71) Applicant (for all designated States except US): AKZO NOBEL N.V. [NL/NL]; P.O. Box 9300, NL-6800 SB Arnhem (NL).			
(71) Applicant (for SE only): EKA CHEMICALS AB [SE/SE]; S-445 80 Bohus (SE).			
(72) Inventors; and (75) Inventors/Applicants (for US only): STRUCK, Oliver [DE/DE]; Oberstrasse 26, D-52349 Düren (DE). HÄLLSTRÖM, Hans [SE/SE]; Knut Stangenbergs väg 162, S-131 47 Nacka (SE). SIKKAR, Rein [SE/SE]; Vesslestigen 2, S-448 34 Floda (SE).			
(74) Agent: NYANDER, Johan; Eka Chemicals AB, Patent Dept., P.O. Box 11556, S-100 61 Stockholm (SE).		(88) Date of publication of the international search report: 16 December 1999 (16.12.99)	
(54) Title: A PROCESS FOR THE PRODUCTION OF PAPER			
(57) Abstract			
<p>The present invention relates to a process for the production of paper from a suspension containing cellulosic fibres, and optional fillers, comprising adding to the suspension drainage and retention aids comprising a cationic organic polymer and anionic microparticulate material, forming and dewatering the suspension on a wire, wherein the cationic organic polymer has a non-aromatic hydrophobic group. The invention further relates to a cationic vinyl addition polymer comprising in polymerized form at least one non-cationic monomer having a non-aromatic hydrophobic group and at least one cationic monomer.</p>			

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/SE 99/00678

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 D21H17/71 C08F220/56 //D21H17:20,D21H17:68,D21H21:10

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 D21H C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 805 234 A (NALCO CHEMICAL CO) 5 November 1997 (1997-11-05) cited in the application page 4, line 27 - line 58 page 7, line 50 - line 54 claims 1,4 ---	1-24
X	EP 0 151 994 A (NALCO CHEMICAL CO) 21 August 1985 (1985-08-21) page 6, line 3 -page 7, line 11 ---	16-24
Y	US 4 250 269 A (BUCKMAN ROBERT H ET AL) 10 February 1981 (1981-02-10) column 1, line 9,10 column 4, line 12 - line 27 ---	1-24
	--- -/--	



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"d" document member of the same patent family

Date of the actual completion of the international search

6 October 1999

Date of mailing of the international search report

04/11/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Naeslund, P

INTERNATIONAL SEARCH REPORT

International Application No

PCT/SE 99/00678

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	EP 0 335 575 A (ALLIED COLLOIDS LTD) 4 October 1989 (1989-10-04) page 3, line 49 - line 55 page 4, line 22,23 ---	1-24
X	WO 95 02088 A (ALLIED COLLOIDS LIMITED) 19 January 1995 (1995-01-19) page 7, line 21 - line 34 page 8, line 35 -page 9, line 3 page 12, line 6 - line 26 claims 1,5 ---	1-24
X	US 5 098 520 A (NALCO CHEMICAL CO) 24 March 1992 (1992-03-24) column 5, line 15 - line 25 column 10, line 30 - line 32 column 4, line 15 - line 45 ---	16-24
A	"Pulp and Paper Manufacture", The Joint Textbook Committee of the Paper Industry, Atlanta, 1991, Third Edition, Vol. 7, "Paper Machine Operations", A. Thorp et al, pages 92-94 XP002117664 -----	14,15

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/SE 99/00678

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0805234 A	05-11-1997	AU 1915897 A	06-11-1997
		BR 9701967 A	15-09-1998
		CA 2204050 A	01-11-1997
		NO 972022 A	03-11-1997
EP 0151994 A	21-08-1985	AT 66028 T	15-08-1991
		AU 577735 B	29-09-1988
		AU 3800485 A	01-08-1985
		BR 8500339 A	03-09-1985
		CS 8500583 A	16-09-1988
		DE 3583688 A	12-09-1991
		DK 34085 A	28-07-1985
		ES 539847 A	01-09-1986
		FI 850296 A,B,	28-07-1985
		GR 850215 A	17-05-1985
		JP 60246893 A	06-12-1985
		MX 166763 B	02-02-1993
		NZ 210958 A	30-08-1988
		CA 1249388 A	24-01-1989
		US 4657946 A	14-04-1987
US 4250269 A	10-02-1981	AR 223041 A	15-07-1981
		AT 376256 B	25-10-1984
		AT 321880 A	15-03-1984
		AU 534541 B	02-02-1984
		AU 5914780 A	04-06-1981
		BE 884478 A	26-01-1981
		BR 8005003 A	09-06-1981
		CA 1150872 A	26-07-1983
		DE 3027126 A	27-05-1981
		ES 495974 A	01-10-1981
		FI 802458 A,B,	27-05-1981
		FR 2470146 A	29-05-1981
		GB 2063892 A,B	10-06-1981
		IN 152695 A	17-03-1984
		IT 1143100 B	22-10-1986
		JP 1514596 C	24-08-1989
		JP 56076451 A	24-06-1981
		JP 63064470 B	12-12-1988
		NL 8002930 A,B,	16-06-1981
		NZ 193787 A	16-03-1982
		PH 16082 A	20-06-1983
		SE 449870 B	25-05-1987
		SE 8005535 A	27-05-1981
		ZA 8003508 A	27-01-1982
EP 0335575 A	04-10-1989	AT 86693 T	15-03-1993
		AU 3174989 A	28-09-1989
		CA 1322435 A	28-09-1993
		DE 68905208 T	07-10-1993
		ES 2053980 T	01-08-1994
		FI 891465 A,B,	29-09-1989
		JP 2006683 A	10-01-1990
		JP 5029719 B	06-05-1993
		JP 5239800 A	17-09-1993
		KR 9602733 B	26-02-1996
		NO 174724 B	14-03-1994
		US 4913775 A	03-04-1990

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/SE 99/00678

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9502088 A	19-01-1995	AT 165407 T	15-05-1998
		AU 696483 B	10-09-1998
		AU 7079194 A	06-02-1995
		BR 9407000 A	03-09-1996
		CA 2166696 A	19-01-1995
		DE 69409808 D	28-05-1998
		DE 69409808 T	13-08-1998
		EP 0707673 A	24-04-1996
		ES 2115238 T	16-06-1998
		FI 960068 A	05-01-1996
		JP 8512364 T	24-12-1996
		NO 960058 A	05-01-1996
		NZ 268058 A	24-10-1997
		US 5514249 A	07-05-1996
US 5098520 A	24-03-1992	AT 114178 T	15-12-1994
		AU 656541 B	09-02-1995
		AU 8831991 A	30-07-1992
		DE 69105193 D	22-12-1994
		DE 69105193 T	18-05-1995
		DK 497030 T	18-04-1995
		EP 0497030 A	05-08-1992
		ES 2067155 T	16-03-1995
		FI 913469 A, B,	26-07-1992
		GR 3014980 T	31-05-1995
		JP 2831165 B	02-12-1998
		JP 4245998 A	02-09-1992
		NO 177394 B	29-05-1995
		US 5185062 A	09-02-1993